

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 939 478 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
01.09.1999 Bulletin 1999/35

(51) Int Cl.⁶: H02K 3/40, H02K 3/34

(21) Application number: 99103611.2

(22) Date of filing: 24.02.1999

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

- Morikawa, Kelichi
Komae-shi, Tokyo 201-0003 (JP)
- Onoda, Mitsuru
Takahagi-shi, Ibaraki-ken 318-0021 (JP)
- Amagi, Shigeo
Naka-gun, Ibaraki-ken 319-1100 (JP)
- Honda, Tatsuo
Hitachinaka-shi, Ibaraki-ken 312-0023 (JP)

(30) Priority: 27.02.1998 JP 4682098

(71) Applicant: Hitachi, Ltd.
Chiyoda-ku, Tokyo 101-8010 (JP)

(74) Representative: Strehl Schübel-Hopf & Partner
Maximilianstrasse 54
80538 München (DE)


(72) Inventors:
• Tsunoda, Tomoya
Hitachi-shi, Ibaraki-ken 316-0032 (JP)

(54) Insulating material and winding for electrical machines

(57) In an insulating material used for the winding of electrical machines, a high thermoconductive insulating film 11 is formed around the outer periphery of the wound conductors 10, using a high thermoconductive


insulating tape 1 which comprises a mica layer 3, a reinforcement layer 5, and a high thermoconductive filler layer 7. The resin content in each of the mica layer 3 and the high thermoconductive filler layer 7 is the range of 10 to 25 % by weight of the total weight of the material.

FIG. 1a



EP 0 939 478 A2

FIG. 2



Description

Background of the invention

5 [0001] The present invention relates to windings for electric rotary machines, furthermore, to insulating material for forming an insulating film for windings of electrical machines.

10 [0002] Conventionally, insulating film for electrical windings used in electric rotary machines have been formed with an insulating material such as, for instance, disclosed in JP-A-63-110929 (1988). That is, the insulating material comprising a mica layer, a reinforcement layer, a filler layer including fillers having a high thermal conductivity therein, and resin contained in each layers has been used. The insulating material was wound around the outer periphery of the wound conductors, and the insulating film for windings of electrical machines was formed by curing the resin in the insulating material under a pressurizing state.

Summary of the invention

15 [0003] The insulating film for windings of electrical machines formed as described above with the insulating material as described above did not have any problem as far as it is used for the electric rotary machines operated with a low voltage. However, when it was used for electric rotary machines operated with a high voltage such as commercial power generators, high voltage motors, and the like, electrical defects have been readily generated, and its electrical characteristics had a tendency to be deteriorated.

20 [0004] In view of the above problems, the inventors of the present invention have studied reasons to make the electrical defects be readily generated. As the result, it was found that the reasons were as follows;

25 [0005] The reason was found that, when forming the insulating film for windings of electrical machines, a part of fine bubbles contained in any of the mica layers, filler layers, and the resin were not removed with a part of the resin containing them, and were remained in the insulating material. And, this was caused by insufficient flow of impregnated resin in the insulating film during the pressurizing process when forming the insulating film for windings of electrical machines, because the resin content in each of the mica layer and the filler layer was not maintained at an appropriate content.

30 [0006] The present invention is aimed at providing windings for electrical machines having insulating film superior in electric characteristics. Furthermore, the present invention is aimed at providing insulating material, which makes it possible to obtain the insulating film for windings of electrical machines superior in electric characteristics.

[0007] The insulating material relating to the present invention comprises a mica layer, a reinforcement layer, and a filler layer, and concurrently, a resin content in each of the mica layer and the filler layer is specified to the range of 10-25 % by weight of total weight of the insulating material.

35 [0008] The mica layer comprises mica flakes and/or mica particles. The reinforcement layer comprises a reinforcing material, for instance, glass cloth. The filler layer comprises a filler having a thermal conductivity of at least 5 W/m²K, for instance, alumina. The insulating material is a laminated body of these layers in the order of the mica layer, the reinforcement layer, and the filler layer, or of the filler layer, the mica layer, and the reinforcement layer.

40 [0009] The insulating material further comprises resin, for instance, epoxy resin. Total content of the resin contained in the insulating material is in the range of 20-50 % by weight of the total weight of the insulating material, and the resin content in each of the mica layer and the filler layer is in the range of 10-25 % by weight of the total weight of the insulating material.

45 [0010] The reason to specify the resin content in each of the mica layer and the filler layer at least 10 % by weight of the total weight of the insulating material is that, when forming the insulating film for windings of electrical machines, it is necessary to make each of the mica layer and the filler layer contain resin of at least 10 % by weight of the total weight of the resin, in order to remove the fine bubbles contained in each of the mica layer and the filler layer in the pressurizing process.

50 [0011] The reason to make the resin content in each of the mica layer and the filler layer equal to or less than 25 % by weight of the total weight of the insulating material is that, if the resin content in each of the mica layer and the filler layer exceeds 25 % by weight of the total weight of the insulating material, an operability in winding the insulating material onto the conductor is decreased, and the insulating material is wrinkled.

[0012] The insulating material relating to the present invention is specified that difference of the resin content in the mica layer from the resin content in the filler layer is equal to or less than 10 % by weight.

55 [0013] The reason to make the difference of the resin content in the mica layer and the resin content in the filler layer equal to or less than 10 % by weight is that, if the difference of the resin content in the mica layer and the resin content in the filler layer exceeds 10 % by weight, a part of the resin containing the fine bubbles to be removed is transferred from the layer having a large resin content to the layer having a small resin content, and is remained therein in the pressurizing process at forming the insulating film for windings of electrical machines.

[0014] In accordance with the windings for electrical machines relating to the present invention, the insulating film is formed with an insulating material comprising a high dielectric strength layer, a reinforcement layer, and a thermoconductive layer, and the resin content in respective of the high dielectric strength layer and the thermoconductive layer is in the range of 10-25 % by weight, respectively, of total weight of the insulating material.

[0015] The high dielectric strength layer is a mica layer comprising mica flakes. The reinforcement layer is a layer comprising a reinforcement material, for instance, glass cloth. The thermoconductive layer is a filler layer comprising a filler having a thermal conductivity of at least 5 W/m•K, for instance, alumina.

[0016] Each of the layers comprises a resin, for instance, epoxy resin. Total resin content is in the range of 20-50 % by weight of the total weight of the insulating material, and the resin content of the each layer of the mica layer and the filler layer is in the range of 10-25 % by weight of the total weight of the insulating material. The difference of the resin content in the mica layer from the resin content in the filler layer is equal to or less than 10 % by weight.

[0017] The reason to adjust the resin content in each of the mica layer and the filler layer to the range 10-25 % by weight of the total weight of the insulating material is to obtain a desired electric characteristics, for instance, alternating insulation breakdown voltage of 26.5-29.0 kV/mm.

[0018] The insulating film for windings of electrical machines is formed using the insulating material as follows;

[0019] First, insulated conductors are wound several times for forming a wound conductor. Then, the insulating material is wound around the outer periphery of the wound conductor so that either of the mica layer, or the filler layer is to be closest to the wound conductor. Subsequently, a releasing agent is applied onto the outer periphery of the insulating material. A shape forming jig is attached to the winding, and an external force is applied from the surface via the jig. Then, the insulating film is formed by heating at a designated temperature for curing the resin in the insulating material with removing the fine bubbles contained in the insulating material with a part of the resin in the insulating material.

Brief description of the drawings

[0020]

FIG. 1 is a cross sectional view indicating the material structure of the high thermoconductive insulating tape of the embodiment of the present invention;

FIG. 2 is a perspective view indicating the structure of the windings for electrical machines of the embodiment of the present invention;

FIG. 3 is a perspective view for explaining a manufacturing process of the windings for electrical machines of the embodiment of the present invention;

FIG. 4 is a cross sectional view of the generator; and

FIG. 5 is a perspective view showing the stator slots.

Detailed explanation of the preferred embodiments of the invention

[0021] Hereinafter, an embodiment of the present invention is explained referring to drawings. A structure of material for the high thermoconductive insulating tape (high thermoconductive preimpregnated tape) of the embodiment of the present invention is explained hereinafter referring to FIG. 1a. The high thermoconductive insulating tape 1 comprises a laminated body, wherein a mica layer 3 (high dielectric strength layer) comprising a small mica flakes sheet 2, a reinforcement layer 5 comprising glass cloth 4, and a high thermoconductive filler layer (thermoconductive layer) comprising alumina particles 6 are laminated in the order of the above description. The laminated body also may be formed by laminating in the order of the high thermoconductive filler layer 7, the mica layer 3, and the reinforcement layer 5 as shown in Fig. 1b.

[0022] The high thermoconductive insulating tape 1 also contains the resin 8 in each of the mica layer 3, the reinforcement layer 5, and the high thermoconductive filler layer 7, and the total content of the resin 8 is 31.4 % by weight of the total weight of the high thermoconductive insulating tape 1. The resin content in the mica layer 3 is 12.9 % by weight of the total weight of the high thermoconductive insulating tape 1, and the resin content in the high thermoconductive filler layer 7 is 15.0 % by weight of the total weight of the high thermoconductive insulating tape 1.

[0023] The high thermoconductive insulating tape 1 was prepared as follows: First, a small mica flakes foil 2 (weight; 165 g/m²) manufactured by a paper making machine with small mica flakes dispersed in water, and a glass cloth 4 (weight; 35 g/m²) were prepared. A resin 8 composed by mixing BF₃ monoethylamine 3 parts by weight into novolak type epoxy resin 100 parts by weight was impregnated into the small mica flakes foil 2 and the glass cloth 4, and a small mica flakes sheet (a laminated body of the mica layer 3 and the reinforcement layer 5) was obtained by adhering the small mica flakes foil 2 and the glass cloth 4.

[0024] The resin 8 composed by mixing BF₃ monoethylamine 3 parts by weight into the novolak type epoxy resin

100 parts by weight, and alumina particles 6 were mixed so that a weight ratio of the alumina particles 6 to the resin 8 became 2:1. After adding methylethylketone of 10 % by weight, the resin was applied onto the side plane of the reinforcement layer 5 of the small mica flakes sheet by a coater so that the applied amount of the resin became 256 g/m². Then, the high thermoconductive insulating sheet was obtained by evaporating and removing the methylethylketone.

[0025] The high thermoconductive insulating tape 1 was obtained by slitting the high thermoconductive insulating sheet to 30 mm wide by a slitter.

[0026] A structure of winding for electrical machines in the embodiment of the present invention is explained hereinafter referring to FIG. 2. The winding for electrical machine 9 comprises a wound conductor 10 formed by winding plural insulating conductors 10a, and high thermoconductive insulating film 11 formed at the outer peripheral portion of the wound conductor 10.

[0027] The windings for electrical machines 9 was prepared as follows: First, a plurality of the insulated conductors 10a are wound several times for forming a wound conductor, as indicated in FIG. 2. Then, the high thermoconductive insulating tape 1 indicated in FIG. 1 was wound around the outer periphery of the wound conductor. At this time, the high thermoconductive insulating tape 1 could be wound irrelevant to either of the mica layer 3, or the high thermoconductive filler layer 7 is closest to the wound conductor 10, but in the present embodiment, the high thermoconductive insulating tape 1 was wound at the outer periphery of the wound conductors 10 so that the mica layer 3 was to be closest to the wound conductor 10. Subsequently, a releasing tape 12 was wound around the outer periphery of the high thermoconductive insulating tape 1. The reason to wind the releasing tape 12 at the outer periphery of the high thermoconductive insulating tape 1 is to prevent a shape forming jig, which would be explained later, from adhering to the high thermoconductive insulating tape 1.

[0028] Subsequently, a shape forming jig was attached to the wound conductor 10 as indicated in FIG. 3, and an external force was applied from the surface via the jig. Then, the high thermoconductive insulating film 11 was formed by heating at a designated temperature for curing the resin 8 in the high thermoconductive insulating tape 1 with removing the fine bubbles contained in the high thermoconductive insulating tape 1 with a part of the resin 14 in the high thermoconductive insulating tape 1, and the winding for electrical machines 9 was obtained.

[0029] The windings 9 for electrical machines of the present embodiment manufactured as above are assembled into core slot of electric rotary machines such as power generators, motors, and the like.

[0030] Figs. 4 and 5 is a cross sectional view showing a generator, and the winding 9 is inserted into slots 50 of the generator. The generator comprises a stator frame 100 supporting a bearing 20, a stator mounted on the stator frame 100 and a rotor composed of a rotor core 60 and rotatably mounted by the bearing 20 in the stator. The stator has a stator core 30, and the winding 9 inserted into the slots 50 is used as a stator coil 40. As shown in Fig.5, the stator coil 40 is assembled into the slots 50 and fixed by a spring 60 of fibrous glass reinforced plastics between the slots 50 and stator coil 40. A sheet 70 and spring 90 of fibrous glass reinforced plastics are sandwiched between a wedge 80 and the stator to fix the stator winding 40 in the slots 50.

[0031] Next, results of tests on the alternating break down voltage of the windings for electric machines of the present embodiment and of windings for electric machines of the comparative example are explained based on Table 1. The windings for electric machines of the comparative example used in the tests were manufactured with high thermoconductive insulation formed by high thermoconductive insulating tape, which was prepared by the following process.

[0032] First, a small mica flakes foil 2(weight; 165 g/m²) manufactured by a paper making machine with small mica flakes dispersed in water, and a glass cloth 4 (weight; 35 g/m²) were prepared. A resin composed by mixing BF₃ monoethylamine 3 parts by weight into novolak type epoxy resin 100 parts by weight was impregnated into the small mica flakes foil 2 and the glass cloth 4, and a small mica flakes sheet (a laminated body of the mica layer 3 and the reinforcement layer 5) was obtained by adhering the small mica flakes foil 2 and the glass cloth 4.

[0033] The resin composed by mixing BF₃ monoethylamine 3 parts by weight to the novolak type epoxy resin 100 parts by weight, and alumina particles were mixed so that a weight ratio of the alumina particles to the resin became 3.5:1. After adding methylethylketone of 10 % by weight, the resin was applied onto the side plane of the reinforcement layer 5 of the small mica flakes sheet by a coater so that the applied amount of the resin became 230 g/m². Then, the high thermoconductive insulating sheet was obtained by evaporating and removing the methylethylketone.

[0034] The high thermoconductive insulating tape 1 was obtained by slitting the high thermoconductive insulating sheet to 30 mm wide by a slitter.

[0035] The total resin content in the high thermoconductive insulating tape of the comparative example manufactured as above was 19.3 % by weight of the total weight of the high thermoconductive insulating tape. The resin content in the mica layer was 19.3 % by weight of the total weight of the high thermoconductive insulating tape, and the resin content in the high thermoconductive filler layer was 10.4 % by weight of the total weight of the high thermoconductive insulating tape.

[0036] The windings for electrical machines 9 was prepared using the high thermoconductive insulating tape manufactured as above. The method of manufacturing was as same as the present embodiment. Its explanation is omitted.

[0037] In the test on the alternating break down voltage, an aluminum foil was wound respectively around the outer periphery of the windings for electrical machines of the present embodiment and of the comparative example as an electrode, and the alternating break down voltages were measured by supplying an alternating voltage between the aluminum electrode and the winding conductor of each of windings for electrical machines. The results were as shown in Table 1.

Table 1

Results of measuring insulation break down voltage		
	Embodiment	Comparative example
Observed	26.5	19.0
values	29.0	17.5
(kV/mm)	27.5	21.5
Average (kV/mm)	27.7	19.3

[0038] As indicated in Table 1, the windings for electric machines of the present embodiment had higher alternating break down voltage than the windings for electric machines of the comparative example. This was, because the high thermoconductive insulating film of the winding for electrical machines was formed using the high thermoconductive insulating tape, wherein the resin content in each of the mica layer and the high thermoconductive filler layer was specified to the range of 10-25 % by weight of the total weight of the material, and because fine bubbles contained in the high thermoconductive insulating tape could be removed sufficiently with a part of the resin in the high thermoconductive tape in the pressurizing process during forming the high thermoconductive insulating film of the windings for electrical machines.

[0039] Accordingly, because the windings for electrical machines of the present embodiment is provided with a dense high thermoconductive insulating film superior in electrical characteristics, a high reliability can be provided to the electric rotary machines operated with a high voltage.

[0040] In accordance with the insulating material relating to the present invention, the high thermoconductive insulating film superior in electrical characteristics can be obtained, because the resin content in each of the mica layer and the high thermoconductive filler layer is specified to the range of 10-25 % by weight of the total weight of the material, and fine bubbles contained in the high thermoconductive insulating tape can be removed sufficiently with a part of the resin in the high thermoconductive tape in the pressurizing process during forming the high thermoconductive insulating film of the windings for electrical machines.

[0041] In accordance with the resin content specified as above, decrease of workability and causing wrinkles to the insulating material during winding the wound conductors with the insulating material can be prevented. Therefore, generation of voids in the insulating film of the windings for electrical machines, which will cause an electrical defect, can be prevented; and the high thermoconductive insulating film superior in electrical characteristics can be obtained.

[0042] In accordance with the insulating material relating to the present invention, the high thermoconductive insulating film superior in electrical characteristics can be obtained. Because difference of the resin content in the mica layer from the resin content in the filler layer is specified equal to 10 % by weight or less, a part of the resin including fine bubbles therein, which should be removed outside, can be prevented from entering and remaining into the one layer of smaller resin content from the other layer of larger resin content.

[0043] In accordance with the windings for electrical machines relating to the present invention, the highly reliable windings for electrical machines having the insulating film superior in electrical characteristics, and the electrical characteristics, which will not be deteriorated even if the windings are used in any electric rotary machines, can be obtained. Because the insulating film is formed using the insulating material, wherein the resin content in each of the mica layer and the high thermoconductive filler layer is specified to the range of 10-25 % by weight of the total weight of the insulating material, fine bubbles contained in the high thermoconductive insulating tape can be removed sufficiently with a part of the resin in the high thermoconductive tape in the pressurizing process during forming the high thermoconductive insulating film of the windings for electrical machines.

[0044] If the insulating film is formed using the insulating material, wherein the resin content is specified to the range as above, decrease of workability and causing generation of wrinkles to the insulating material during winding the wound conductors with the insulating material can be prevented. Therefore, generation of voids in the insulating film of the windings for electrical machines, which will cause an electrical defect, can be prevented; and the highly reliable windings for electrical machines having the high thermoconductive insulating film superior in electrical characteristics, and the electrical characteristics, which will not be deteriorated even if the windings are used in any electric rotary

machines, can be obtained.

[0045] In accordance with the windings for electrical machines relating to the present invention, its insulating film is formed using the insulating material; wherein, because the difference of the resin content in the mica layer from the resin content in the filler layer is specified equal to 10 % by weight or less, a part of the resin including fine bubbles therein, which should be removed outside, can be prevented from entering and remaining into the one layer of smaller resin content from the other layer of larger resin content; and the highly reliable windings for electrical machines having the high thermoconductive insulating film superior in electrical characteristics, and the electrical characteristics, which will not be deteriorated even if the windings are used in any electric rotary machines, can be obtained.

Claims

1. An insulating material comprising a mica layer (3), a reinforcement layer (5), and a filler layer (7), wherein the resin content in said mica layer (3) and in said filler layer (7) is in the range of 10 to 25 % by weight of the total weight of said insulating material.
2. The insulating material of claim 1, wherein the resin content in said mica layer (3) differs from that in said filler layer (7) by 10 % by weight or less.
3. The insulating material of claim 1, wherein the resin contents in the mica layer (3) and in the filler layer (7) are substantially equal.
4. The insulating material of claim 1, wherein the total resin content in said insulating material is in the range of 20 to 50 % by weight of the total weight of said insulating material.
5. The insulating material of claim 1, wherein said filler layer (7) comprises a filler material having a thermal conductivity of at least 5 W/m•K.
6. A winding for electrical machines comprising a high dielectric-strength layer (3), a reinforcement layer (5), and a thermoconductive layer (7), wherein the resin content in said high dielectric-strength layer (3) and in said thermoconductive layer (7) is in the range of 10 to 25 % by weight of the total weight of its insulating material, and wherein an insulating film (11) is formed so that said high dielectric-strength layer (3) of said insulating material is placed closer to a wound conductor (10) than said thermoconductive layer (7) and said reinforcement layer (5).
7. A winding for electrical machines comprising a high dielectric-strength layer (3), a reinforcement layer (5), and a thermoconductive layer (7), wherein the resin content in said high dielectric-strength layer (3) and in said thermoconductive layer (7) is in the range of 10 to 25 % by weight of the total weight of its insulating material, and wherein an insulating film (11) is formed so that said thermoconductive layer (7) of said insulating material is placed closer to a wound conductor (10) than said high dielectric-strength layer (3) and said reinforcement layer (5).
8. A winding for electrical machines comprising an insulating film (11) comprising a high dielectric-strength layer (3), a reinforcement layer (5), and a thermal conductive layer, wherein the alternating insulation breakdown voltage of said insulating film (11) is set in the range of 26.5 to 29.0 kV/mm by adjusting the resin content in said high dielectric-strength layer (3) and in said thermal conductive layer.
9. A winding for electrical machines comprising an insulating film (11) composed of an insulating material according to any one of claims 1 to 5.
10. An electric rotary machine provided with a winding according to any one of claim 6 to claim 9.
11. An insulating material comprising
 - a reinforcement layer (5) having two surfaces,
 - a mica layer (3) formed on one surface of said reinforcement layer (5), and
 - a filler layer (7) formed on the other surface of said reinforcement layer (5), or on said mica layer (3), after lamination of said reinforcement and mica layers (5, 3), wherein the resin content in said mica layer (3) and in said filler layer (7) is in the range of 10 to 25 % by weight of the total weight of said insulating material.

FIG. 1a




FIG. 1b




FIG. 2




FIG. 3




FIG. 4





FIG. 5



(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 939 478 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
29.03.2000 Bulletin 2000/13

(51) Int Cl.7: **H02K 3/40**, H02K 3/34,
H02K 3/30, H01B 3/00

(43) Date of publication A2:
01.09.1999 Bulletin 1999/35

(21) Application number: 99103611.2

(22) Date of filing: 24.02.1999

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

- Morikawa, Keiichi
Komae-shi, Tokyo 201-0003 (JP)
- Onoda, Mitsuru
Takahagi-shi, Ibaraki-ken 318-0021 (JP)
- Amagi, Shigeo
Naka-gun, Ibaraki-ken 319-1100 (JP)
- Honda, Tatsuo
Hitachinaka-shi, Ibaraki-ken 312-0023 (JP)

(30) Priority: 27.02.1998 JP 4682098

(71) Applicant: Hitachi, Ltd.
Chiyoda-ku, Tokyo 101-8010 (JP)

(74) Representative: Strehl Schübel-Hopf & Partner
Maximilianstrasse 54
80538 München (DE)


(72) Inventors:
• Tsunoda, Tomoya
Hitachi-shi, Ibaraki-ken 316-0032 (JP)

(54) Insulating material and winding for electrical machines

(57) In an insulating material used for the winding of electrical machines, a high thermoconductive insulating film 11 is formed around the outer periphery of the wound conductors 10, using a high thermoconductive


insulating tape 1 which comprises a mica layer 3, a reinforcement layer 5, and a high thermoconductive filler layer 7. The resin content in each of the mica layer 3 and the high thermoconductive filler layer 7 is the range of 10 to 25 % by weight of the total weight of the material.

FIG. 1a



EP 0 939 478 A3

FIG. 2





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 10 3611

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
D,X	EP 0 266 602 A (ASEA AB) 11 May 1988 (1988-05-11) * column 1, line 41 - line 46 * * column 3, line 1 - line 9 * * column 3, line 24 - line 26 * & JP 63 110929 A (ASEA AB) 16 May 1988 (1988-05-16) ---	1,4,5, 9-11	H02K3/40 H02K3/34 H02K3/30 H01B3/00
A	US 4 356 417 A (SMITH JAMES D B ET AL) 26 October 1982 (1982-10-26) * column 11, line 63 - line 68 * ---		
A	EP 0 012 566 A (HITACHI LTD) 25 June 1980 (1980-06-25) * page 6, line 2 - line 7 * ---		
A	US 4 286 010 A (STALEY RONALD W ET AL) 25 August 1981 (1981-08-25) * column 4, line 48 - line 61 * * column 7, line 34 - line 45 * * figure 7 * -----		
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			H02K H01B
The present search report has been drawn up for all claims			
Place of search BERLIN		Date of completion of the search 7 February 2000	Examiner Foussier, P
CATEGORY OF CITED DOCUMENTS		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			

EPO FORM 1503 03/82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 10 3611

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

07-02-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0266602 A	11-05-1988	SE 455246 B	27-06-1988
		AT 85474 T	15-02-1993
		CA 1289610 A	24-09-1991
		DE 3784008 A	18-03-1993
		JP 63110929 A	16-05-1988
		SE 8604509 A	23-04-1988
		US 4806806 A	21-02-1989
US 4356417 A	26-10-1982	US 4296018 A	20-10-1981
		BR 8003070 A	23-12-1980
		CA 1152676 A	23-08-1983
		FR 2456760 A	12-12-1980
		IN 153135 A	02-06-1984
		IT 1140952 B	10-10-1986
		JP 1120234 C	28-10-1982
		JP 55152718 A	28-11-1980
		JP 57011565 B	05-03-1982
		KR 8401788 B	20-10-1984
		SE 8003672 A	18-11-1980
EP 0012566 A	25-06-1980	JP 1328533 C	30-07-1986
		JP 55079641 A	16-06-1980
		JP 60055971 B	07-12-1985
		AU 516801 B	25-06-1981
		AU 5347179 A	12-06-1980
		CA 1133975 A	19-10-1982
		ZA 7906573 A	26-11-1980
US 4286010 A	25-08-1981	AU 539365 B	20-09-1984
		AU 6483080 A	28-04-1981
		BE 885550 A	02-02-1981
		CA 1157323 A	22-11-1983
		CH 646813 A	14-12-1984
		DE 3049940 C	21-01-1988
		EP 0036429 A	30-09-1981
		GB 2081732 A,B	24-02-1982
		JP 56501698 T	19-11-1981
		JP 62040806 B	31-08-1987
		WO 8100986 A	16-04-1981

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82